

Bottom-Rolling Sliding Door and Lift-Slide Door

7/8" OA

Glass: PPG and Pilkington

Spacer: Technoform TGI spacer

Gas fill: Air

No Grid	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	151-1	0.47	0.59	0.65	153-1	0.46	0.55	0.63	155-1	0.49	0.54	0.62
SB60 over clear	157-1	0.44	0.35	0.62	159-1	0.43	0.34	0.61	161-1	0.46	0.34	0.60
SB60 over EA	169-1	0.38	0.33	0.58	171-1	0.38	0.32	0.56	173-1	0.40	0.32	0.55
SB70 over clear	175-1	0.43	0.24	0.55	177-1	0.43	0.24	0.54	179-1	0.45	0.24	0.55
SB70 over EA	187-1	0.38	0.23	0.51	189-1	0.37	0.23	0.50	191-1	0.40	0.23	0.50

SDL	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	151-2	0.47	0.53	0.57	153-2	0.46	0.48	0.56	155-2	0.49	0.47	0.55
SB60 over clear	157-2	0.44	0.31	0.54	159-2	0.43	0.31	0.53	161-2	0.46	0.31	0.53
SB60 over EA	169-2	0.38	0.30	0.51	171-2	0.38	0.29	0.50	173-2	0.40	0.29	0.49
SB70 over clear	175-2	0.43	0.22	0.48	177-2	0.43	0.22	0.47	179-2	0.45	0.22	0.48
SB70 over EA	187-2	0.38	0.21	0.45	189-2	0.37	0.21	0.44	191-2	0.40	0.21	0.44

TDL	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	152-1	0.59	0.46	0.50	154-1	0.59	0.43	0.49	156-1	0.62	0.42	0.48
SB60 over clear	158-1	0.57	0.27	0.47	160-1	0.57	0.27	0.47	162-1	0.59	0.27	0.46
SB60 over EA	170-1	0.53	0.26	0.44	172-1	0.53	0.26	0.43	174-1	0.55	0.26	0.43
SB70 over clear	176-1	0.56	0.19	0.42	178-1	0.56	0.19	0.41	180-1	0.59	0.19	0.42
SB70 over EA	188-1	0.52	0.18	0.39	190-1	0.53	0.18	0.38	192-1	0.55	0.18	0.39

SDL = simulated divided lite, TDL = true divided lite

EA = Pilkington Energy Advantage, SB60 = PPG Solarban 60, SB70 = PPG Solarban 70

Primary coating on surface 2, secondary coating on surface 4, 1/8" = 3mm, 3/16" = 5mm, 1/4" = 6mm

Bottom-Rolling Sliding Door and Lift-Slide Door

7/8" OA

Glass: PPG and Pilkington

Spacer: Technoform TGI spacer

Gas fill: Argon

No Grid	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	223-1	0.44	0.59	0.65	225-1	0.43	0.55	0.63	227-1	0.44	0.53	0.62
SB60 over clear	229-1	0.40	0.34	0.62	231-1	0.39	0.34	0.61	233-1	0.41	0.34	0.60
SB60 over EA	241-1	0.36	0.33	0.58	243-1	0.35	0.32	0.56	245-1	0.36	0.32	0.55
SB70 over clear	247-1	0.39	0.24	0.55	249-1	0.39	0.24	0.54	251-1	0.40	0.24	0.55
SB70 over EA	259-1				261-1				263-1			

SDL	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	223-2	0.44	0.53	0.57	225-2	0.43	0.48	0.56	227-2	0.44	0.47	0.55
SB60 over clear	229-2	0.40	0.31	0.54	231-2	0.39	0.30	0.53	233-2	0.41	0.30	0.53
SB60 over EA	241-2	0.36	0.30	0.51	243-2	0.35	0.29	0.50	245-2	0.36	0.29	0.49
SB70 over clear	247-2	0.39	0.21	0.48	249-2	0.39	0.21	0.47	251-2	0.40	0.22	0.48
SB70 over EA	259-2				261-2				263-2			

TDL	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	224-1	0.57	0.46	0.50	226-1	0.57	0.43	0.49	228-1	0.58	0.42	0.48
SB60 over clear	230-1	0.54	0.27	0.47	232-1	0.54	0.27	0.47	234-1	0.56	0.27	0.46
SB60 over EA	242-1	0.50	0.26	0.44	244-1	0.51	0.26	0.43	246-1	0.53	0.25	0.43
SB70 over clear	248-1	0.53	0.19	0.42	250-1	0.54	0.19	0.41	252-1	0.56	0.19	0.42
SB70 over EA	260-1				262-1				264-1			

SDL = simulated divided lite, TDL = true divided lite

EA = Pilkington Energy Advantage, SB60 = PPG Solarban 60, SB70 = PPG Solarban 70

Primary coating on surface 2, secondary coating on surface 4, 1/8" = 3mm, 3/16" = 5mm, 1/4" = 6mm

Bottom-Rolling Sliding Door and Lift-Slide Door

1 1/8" OA

Glass: PPG and Pilkington

Spacer: Technoform TGI spacer

Gas fill: Air

No Grid	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	295-1	0.47	0.59	0.65	297-1	0.47	0.55	0.63	299-1	0.46	0.53	0.62
SB60 over clear	301-1	0.44	0.35	0.62	303-1	0.44	0.34	0.61	305-1	0.43	0.34	0.60
SB60 over EA	313-1	0.38	0.33	0.58	315-1	0.38	0.32	0.56	317-1	0.37	0.32	0.55
SB70 over clear	319-1	0.44	0.24	0.55	321-1	0.43	0.24	0.54	323-1	0.43	0.24	0.55
SB70 over EA	331-1	0.38	0.23	0.51	333-1	0.37	0.23	0.50	335-1	0.37	0.23	0.50

SDL	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	295-2	0.47	0.53	0.57	297-2	0.47	0.48	0.56	299-2	0.46	0.47	0.55
SB60 over clear	301-2	0.44	0.31	0.54	303-2	0.44	0.30	0.53	305-2	0.43	0.30	0.53
SB60 over EA	313-2	0.38	0.30	0.51	315-2	0.38	0.29	0.50	317-2	0.37	0.29	0.49
SB70 over clear	319-2	0.44	0.22	0.48	321-2	0.43	0.22	0.47	323-2	0.43	0.21	0.48
SB70 over EA	331-2	0.38	0.21	0.45	333-2	0.37	0.20	0.44	335-2	0.37	0.20	0.44

TDL	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	296-1	0.57	0.46	0.50	298-1	0.57	0.43	0.49	300-1	0.57	0.42	0.48
SB60 over clear	302-1	0.55	0.27	0.47	304-1	0.54	0.27	0.47	306-1	0.55	0.27	0.46
SB60 over EA	314-1	0.51	0.26	0.44	316-1	0.51	0.26	0.43	318-1	0.51	0.25	0.43
SB70 over clear	320-1	0.54	0.19	0.42	322-1	0.54	0.19	0.41	324-1	0.54	0.19	0.42
SB70 over EA	332-1	0.50	0.18	0.39	334-1	0.50	0.18	0.38	336-1	0.51	0.18	0.39

SDL = simulated divided lite, TDL = true divided lite

EA = Pilkington Energy Advantage, SB60 = PPG Solarban 60, SB70 = PPG Solarban 70

Primary coating on surface 2, secondary coating on surface 4, 1/8" = 3mm, 3/16" = 5mm, 1/4" = 6mm

Bottom-Rolling Sliding Door and Lift-Slide Door

1 1/8" OA

Glass: PPG and Pilkington

Spacer: Technoform TGI spacer

Gas fill: Argon

No Grid	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	367-1	0.44	0.59	0.65	369-1	0.43	0.55	0.63	371-1	0.43	0.53	0.62
SB60 over clear	373-1	0.40	0.34	0.62	375-1	0.40	0.34	0.61	377-1	0.39	0.33	0.60
SB60 over EA	385-1	0.35	0.33	0.58	387-1	0.35	0.32	0.56	389-1	0.35	0.32	0.55
SB70 over clear	391-1	0.40	0.24	0.55	393-1	0.39	0.24	0.54	395-1	0.39	0.24	0.55
SB70 over EA	403-1	0.35	0.23	0.51	405-1	0.35	0.23	0.50	407-1	0.34	0.23	0.50

SDL	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	367-2	0.44	0.53	0.57	369-2	0.43	0.48	0.56	371-2	0.43	0.47	0.55
SB60 over clear	373-2	0.40	0.31	0.54	375-2	0.40	0.30	0.53	377-2	0.39	0.30	0.53
SB60 over EA	385-2	0.35	0.30	0.51	387-2	0.35	0.29	0.50	389-2	0.35	0.29	0.49
SB70 over clear	391-2	0.40	0.21	0.48	393-2	0.39	0.21	0.47	395-2	0.39	0.21	0.48
SB70 over EA	403-2	0.35	0.21	0.45	405-2	0.35	0.20	0.44	407-2	0.34	0.20	0.44

TDL	Glass Thickness											
	1/8" over 1/8"				3/16" over 3/16"				1/4" over 1/4"			
Glazing Type	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT	Prod No	U-Factor	SHGC	VT
EA over clear	368-1	0.54	0.46	0.50	370-1	0.54	0.43	0.49	372-1	0.55	0.42	0.48
SB60 over clear	374-1	0.52	0.27	0.47	376-1	0.52	0.27	0.47	378-1	0.52	0.26	0.46
SB60 over EA	386-1	0.48	0.26	0.44	388-1	0.48	0.26	0.43	390-1	0.49	0.25	0.43
SB70 over clear	392-1	0.51	0.19	0.42	394-1	0.51	0.19	0.41	396-1	0.52	0.19	0.42
SB70 over EA	404-1	0.48	0.18	0.39	406-1	0.48	0.18	0.38	408-1	0.49	0.18	0.39

SDL = simulated divided lite, TDL = true divided lite

EA = Pilkington Energy Advantage, SB60 = PPG Solarban 60, SB70 = PPG Solarban 70

Primary coating on surface 2, secondary coating on surface 4, 1/8" = 3mm, 3/16" = 5mm, 1/4" = 6mm